



14700 Downey Avenue  
 P.O. Box 1418  
 Paramount, CA 90723-1418  
 (562) 531-2060

**PRODUCT SPECIFICATIONS**

**PRODUCT:** LIQUID ASPHALT

**GRADE:** MC-250 **PRODUCT CODE:** 13320

**DESCRIPTION:** A steam refined asphalt cut back with kerosene. Not legal in the SCAQMD. Check local environmental regulations.

**MEETS SPECIFICATIONS:** ASTM D2027  
 AASHTO M82

TESTS	ASTM METHOD	AASHTO METHOD	SPECS.	TYPICAL ANALYSIS <sup>1</sup>
Kinematic Viscosity, 140°F, cSt	D2170	T201	250-500	370
Flash Point, T.O.C., °F	D3143	T79	150 min	200
API Gravity, 60°F	D287			14.2
Density, 60°F, lbs/Gallon	D287			8.09
Water, vol. %	D95	T55	0.2 max	0.0
Distillation Test:	D402	T78		
Vol.% of Total Distillate to 680°F:				
To 437°F			10 max	0
To 500°F			15-55	29
To 600°F			60-87	78
Residue from Distillation, Vol. %			67 min	75
Tests on residue from Distillation:				
Viscosity, 140°F, Poise	D2171	T202	300-1200	1080
Ductility, 77°F, cm	D113	T51	100 min	150+
Solubility in TCE, wt.%	D2042	T44	99.0 min	99.9

<sup>1</sup>Values shown as typical may, at times, be superseded by results which are current at a particular time.

**AVAILABILITY:** Readily available by computerized truck blending

**DOT SHIPPING NAME:** NA1999, Hot asphalt, cutback, 3, III

**DOT PLACARD:** Class 3, Hot, 1999

**RELEASED:** 02-01-2003