



14700 Downey Avenue  
P.O. Box 1418  
Paramount, CA 90723-1418  
(562) 531-2060

**PRODUCT SPECIFICATIONS**

**PRODUCT:** LIQUID ASPHALT

**GRADE:** SC-250 **PRODUCT CODE:** 13360

**DESCRIPTION:** A steam refined asphalt cut back with diesel fuel. May be used in prime coats and cold laid plant mix paving techniques. Meets the requirements of SCAQMD Rule 1108.

**MEETS SPECIFICATIONS:** ASTM D2026  
FEDERAL SS-A-671C

TESTS	ASTM METHOD	AASHTO METHOD	SPECS.	TYPICAL ANALYSIS <sup>1</sup>
Kinematic Viscosity, 140°F, cSt	D2170	T201	250-500	390
Flash Point, C.O.C., °F	D92	T48	175 min	250
API Gravity, 60°F	D287			13.4
Density, 60°F, lbs/Gallon	D287			8.13
Water, vol. %	D95	T55	0.5 max	0.0
Solubility in trichloroethylene, %	D2042	T44	99.0 min	99.9
Distillation Test:	D402	T78		
Total Distillate to 500°F, %	D402	T78	0.5 max	0
Total Distillate to 680°F, %	D402	T78	4-20	18
Viscosity of Residue, 140°F, St	D2170	T201	8-100	65
Asphalt Residue Test:	D243	T56		
Residue of 100 Penetration,%	D5	T49	60 min	72
Ductility of 100 Pen. Res., cm	D113	T51	100 min	150+

<sup>1</sup>Values shown as typicals may, at times, be superseded by results which are current at a particular time.

**AVAILABILITY:** Readily available by computerized truck blending

**DOT SHIPPING NAME:** NA1999, Hot asphalt, cutback, 3, III

**DOT PLACARD:** Class 3, Hot, 1999

**RELEASED:** 02-01-2003