



**Aug. 19th to 24th,
PG76-22TR with 18% TR content
Caltrans Dist 9, Hwy 395
Between Topaz (State line) and Walker,
Application rate 0.32-0.38 gals/syd,
Pre-coated chip 5/16 applied at 24 lbs/syd.
fogged with CQS and sand.**



Pavement condition before treatment

Aug-2010



Chip application

Aug-2010



PG76-22TR (18% tire rubber)
application

Aug-2010



11-18-10



11-18-10

