



14700 Downey Avenue  
P.O. Box 1418  
Paramount, CA 90723-1418  
(562) 531-2060

**PRODUCT SPECIFICATIONS**

**PRODUCT:** EMULSIFIED ASPHALT

**GRADE:** TRMSS **PRODUCT CODE:** 13642

**DESCRIPTION:** "Clay Stabilized" Liquid Tire Rubber Modified Surface Sealer

**MEETS SPECIFICATIONS:** Paramount Petroleum

TESTS	ASTM METHOD	AASHTO METHOD	SPECS.	TYPICAL ANALYSIS <sup>1</sup>
Viscosity, Saybolt, °F, SFS	D244	T59	150-300	200
Sieve Test, %	D244	T59	0.1 max	0.01
Density, 60°F, lbs/gallon	D244	T59		8.51
Residue by Evaporation	D244	T59	35 min	40
Exposure, Q.U.V., hours			450 min	600+
Tests on residue from Evaporation:				
Ground Whole Tire Rubber, %	Certificate of Compliance			
Softening Point, °F	D36	T53	140 min	145
Penetration, 25°C, 100g, 5s	D5	T49	20-40	23
Ductility, 25°C, 5cm/m, cm	D133	T51	20 min	50+
Solubility %	D2042	T44	94.5 min	97.5

<sup>1</sup>Values shown as typicals may, at times, be superseded by results which are current at a particular time.

**AVAILABILITY:** Upon request

**DOT SHIPPING NAME:** Asphalt, non-hazardous

**DOT PLACARD:** None required

**RELEASED:** 05-23-2003